ROCAL Adhesive Films

Polymeric White Gloss Perm 5 Yr Self Adhesive Graphics SPVO-P



ROCAL Polymeric vinyls have been engineered for a large range of wide format digitally printed mounted graphic applications using face stock weights & formulations that consistently capture and display ink effectively whilst providing extra long term durability & excellent resistance to shrinkage. SPVO-P is a glossy opaque white film with a permanent, solvent based acrylic adhesive which can be wet applied and has a two side coated, moisture resistant & stay-flat paper liner.





Premium



Calandered PVC film, adhesive & release paper Composition:

Main Applications: Long term permanent mounted graphics

Features: Controlled, reliable print formulation & shrinkage, stay-flat liner Benefits: Reliable printing, high durability & flatness, visually appealing

Formulation: Plasticised Polymeric Vinyl Storage Conditions: 5~40°C & 35~75% RH

Shelf Life: 1 year from date of manufacture Release Liner: 0.18mm, 120gsm double PE coated Adhesive Type: Clear permanent solvent based acrylic

Total weight including liner & adhesive 320gsm Remarks:



Quality & Testing

• Durability ISO 4892-3 (1000hr)

Application

· Long term adhesive graphics

Manufacturing

ISO9001



• 320 grams per m² ± 5%

Stock Availability

Sheet Sizes: See sheet cutting Roll Widths (mm): 1020, 1370 & 1524

Roll Lengths (mtrs): 50 & 250

Log Cutting: Available for 50m rolls only

Standard Core: 76mm for 50m and 152mm for 250m

Sheet Cutting: Up to 3200mm x 1524mm





10 years



5 years



Heavy Metal Free

No

Recyclable

No

Safety Compliance

RoHs



Printing

Method: UV Offset, Screen & Digital One, wound facing outside of roll

Ink Suitability: UV Cured inks (Offset, Screen & Inkjet) Solvent & Latex

Basic Physical Data

Thickness: 305 micron

Weight: 320 grams per m² ± 5%

Gloss Level: Gloss



Heat Resistance: 80°C Cold Resistance: -30°C

Shrinkage: 0.5 ↓ % (80°Cx48hrs)





ROCAL Adhesive Films

Polymeric White Gloss Perm 5 Yr Self Adhesive Graphics SPVO-P



Physical Characteristics

 $\textbf{Holding Power} \ \ 0.3 \downarrow mm \ (JIS \ Z \ 0237)$

Ball Tack 6 ~ 12

1800 Peel 1800 ↑ g/25mm-24Hr (JIS Z 0237)

Adhesion

90° Release 40±20 g/50mm (JIS Z 0237)

Force

Thickness Film 100micron, Liner 180micron,

Adhesive 25micron

Weight 320 grams per m² \pm 5% Tensile 2000 \uparrow g/10mm (JIS Z 0237)

Strength

Elongation at 150 ↑% (JIS Z 0237)

Break

Gloss Level 80↑ Degree/60°Angle (ISO 2813)

Surface Finish Gloss

UV Stabilized Yes, to maximum concentration



Cuttin	ıg	/
Weldi	ng	X
Foldir	ng	X
Gluing	g	/
Eyelet	tting	\
Stitch	ing	X
Lamin	nating	/
Bendi	ng	X
Routin	ng	X
Punch	ning	\
Drillin	g	\
Screw	/ing	/
V-Gro	oving	X